

This Page Is Inserted by IFW Operations
and is not a part of the Official Record

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images may include (but are not limited to):

- BLACK BORDERS
- ✓• TEXT CUT OFF AT TOP, BOTTOM OR SIDES
- ✓• FADED TEXT
- ILLEGIBLE TEXT
- SKEWED/SLANTED IMAGES
- COLORED PHOTOS
- BLACK OR VERY BLACK AND WHITE DARK PHOTOS
- GRAY SCALE DOCUMENTS

IMAGES ARE BEST AVAILABLE COPY.

**As rescanning documents *will not* correct images,
please do not report the images to the
Image Problem Mailbox.**

PATENT ABSTRACTS OF JAPAN

(11)Publication number : 02-120372
 (43)Date of publication of application : 08.05.1990

(51)Int.Cl. C09D 5/14
 C09D 5/02



(21)Application number : 63-272655 (71)Applicant : KAO CORP
 (22)Date of filing : 28.10.1988 (72)Inventor : IWASAKI TETSU HARU
 HIOKI YUICHI
 MITOBE HIROYUKI

(54) MILDEWPROOFING COATING COMPOSITION

(57)Abstract:

PURPOSE: To provide a mildewproofing coating composition having an excellent fungicidal effect and high safety and can sustain a mildewproofing effect for a long time by mixing a synthetic resin emulsion with a specified quat. ammonium salt in a specified mixing ratio.

CONSTITUTION: At least 0.1 pt.wt. quat. ammonium salt of formula I (wherein at least one of R₁, R₂ and R₃ is an 8-30C linear or branched alkyl or alkenyl, and the rest are methyl, ethyl, formula II of formula III; R₄ is methyl or ethyl; and the counter ion X⁻¹ is an anionic residue of an acid having a 7C or higher hydrophobic group) is added to 100 pts.wt. (in terms of nonvolatiles) synthetic resin emulsion (e.g., vinyl chloride resin emulsion) to produce a mildewproofing coating composition. Examples of the counter ion of the quat. ammonium salt of formula I include residues of dodecylbenzenesulfonic acid and lauric acid.



II



III

LEGAL STATUS

[Date of request for examination]

[Date of sending the examiner's decision of rejection]

[Kind of final disposal of application other than the examiner's decision of rejection or application converted registration]

[Date of final disposal for application]

[Patent number]

[Date of registration]

[Number of appeal against examiner's decision of rejection]

[Date of requesting appeal against examiner's decision of rejection]

AN 1990:554360 HCAPLUS

DN 113:154360

TI Microbicidal coating compositions containing quaternary ammonium salts

IN Iwasaki, Tetsuharu; Hioki, Yuichi; Mitobe, Hiroyuki

PA Kao Corp., Japan

SO Japan Kokai Tokkyo Koho, 5 pp.

CODEN: JKXXAF

DT Patent

LA Japanese

FAN.CNT 1

	PATENT NO.	KIND	DATE	APPLICATION NO.	DATE
PI	JP 02120372	A2	19900508	JP 1988-272655	19881028
	JP 2582418	B2	19970219		

OS MARPAT 113:154360

AB The title compns., having prolonged microbicidal effects, comprise synthetic resin emulsions and quaternary ammonium compds. R1N+R2R3R4 X- (1 of R1-3 = C8-30 alkyl or alkenyl with the remainder being = Me, Et, CH2Ph, or 4-pyridylmethyl; R4 = Me, Et; X = anion of acid having C7 hydrophobic group). A fungicidal coating composition contained TiO2 23.4, CaCO3 13.7, clay 6.3, ethylene glycol 1.8, diisobutylene-maleic anhydride copolymer salt 0.5, H2O 13.0, hydroxyethyl cellulose 13.5, acrylic-styrene copolymer emulsion 23.3, defoamer 0.05, and didecyldimethylammonium dodecylbenzenesulfonate 0.5 part.